

AD-A158 658

BORON-NITROGEN POLYMERS(U) ULTRASYSTEMS INC IRVINE CA  
K L PACIOREK ET AL. 01 JUL 85 SN-2022-F  
N00014-82-C-0402

1/1

UNCLASSIFIED


F/G 11/2

NL

END

FILMED

DTIC



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

# AD-A158 658

1a. REPORT SECURITY CLASSIFICATION Unclassified		1b. RESTRICTIVE MARKINGS None	
2a. SECURITY CLASSIFICATION AUTHORITY		2. DISTRIBUTION/AVAILABILITY OF REPORT This document has been approved for public release and sale; its distribution is unlimited.	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE		5. MONITORING ORGANIZATION REPORT NUMBER(S)	
4. PERFORMING ORGANIZATION REPORT NUMBER(S) SN-2022-F		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6a. NAME OF PERFORMING ORGANIZATION Ultrasystems, Inc.	6b. OFFICE SYMBOL (If applicable)	7b. ADDRESS (City, State and ZIP Code) 800 North Quincy Street Arlington, Virginia 22217	
6c. ADDRESS (City, State and ZIP Code) 16845 Von Karman Avenue Irvine, California 92714		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-82-C-0402	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8b. OFFICE SYMBOL (If applicable)	10. SOURCE OF FUNDING NOS.	
8c. ADDRESS (City, State and ZIP Code) 800 North Quincy Street Arlington, Virginia 22217		PROGRAM ELEMENT NO.	PROJECT NO.
11. TITLE (Include Security Classification) Boron-Nitrogen Polymers		TASK NO.	
12. PERSONAL AUTHOR(S) K. L. Paciorek, D. H. Harris, R. H. Kratzer, M. E. Smythe, and P. F. Kimble		WORK UNIT NO.	
13a. TYPE OF REPORT Final	13b. TIME COVERED FROM 1 Jul 82 TO 30 Jun 85	14. DATE OF REPORT (Yr., Mo., Day) 1 July 1985	
15. PAGE COUNT			
16. SUPPLEMENTARY NOTATION			
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB. GR.	
19. ABSTRACT (Continue on reverse if necessary and identify by block number) The objective was to develop processible preceramic polymers amenable to transformation into pure boron nitride for potential applications as fibers and coatings. A series of alkyl, aryl, and trimethylsilyl-substituted borazines was synthesized and subjected to pyrolysis to determine the type of substituent leading to an optimum preceramic polymer. The feasibility of the process was established. From trimethylsilyl-substituted precursors, following stepwise pyrolysis, fibers were drawn and cured in an ammonia atmosphere giving pure boron nitride. Mechanisms responsible for borazine condensations were elucidated; processes involved in precursor synthesis were investigated.			
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS <input type="checkbox"/>		21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL K. L. Paciorek		22b. TELEPHONE NUMBER (Include Area Code) 714-863-7000, ext 561	22c. OFFICE SYMBOL

## SUMMARY OF WORK ACCOMPLISHED

A series of borazines, namely B-trichloro-N-triphenylborazine, B-triamino-N-trimethylborazine, B-triamino-N-triphenylborazine, B-trianilinoborazine, B-trichloro-N-tris(trimethylsilyl)borazine, B-triamino-N-tris(trimethylsilyl)borazine, and B-tris[di(trimethylsilyl)amino]borazine was synthesized. All the materials were evaluated as potential candidate monomers for preceramic polymer formation. The halo-substituted materials yielded exclusively glassy products; the alkyl-substituted members of the series, due to their ease of sublimation and preferential ammonia elimination, did not appear to be promising precursors of boron-nitride systems; the pyrolysis products of the aromatic group containing borazines (both homo- and copolymers) exhibited high melting points even at low degree of polymerization. B-Tris[di(trimethylsilyl)amino]borazine was recovered unchanged following exposure to 400°C. Pyrolysis up to 1000°C of the phenyl-substituted borazines did not afford carbon-free boron nitride. The highest combined weight loss of 66.7% registered by the trianilinoborazine was significantly lower than the 79.0% required for boron nitride formation. In all the instances, the residues were black pointing to the presence of carbon. These results were contrary to the claims made in patent literature. Preceramic polymers amenable to fiber drawing were obtained from B-triamino-N-tris(trimethylsilyl)borazine on pyrolysis at 65-227°C. Further pyrolysis and cure in an ammonia atmosphere at 65-970°C resulted in pure boron-nitride fibers.

The early stages of the polymerization process, both in the trimethylsilyl and phenyl-substituted borazines, were found to occur in a stepwise fashion accompanied by ring opening and closing giving what appears to be fused alternating six- and four-membered ring systems. The operative mechanisms

DTIC FILE COPY

DTIC  
ELECTE  
S AUG 29 1985 D  
G

1

85

8

18

0.1

DISTRIBUTION STATEMENT A  
Approved for public release;  
Distribution Unlimited

were elucidated, based on the volatiles evolved (nature and quantities) and telomers formed (molecular weight, composition, and spectral characteristics).

In addition, efforts were expended at synthesis of other trimethylsilyl-substituted borazines and precursors. Types of products formed were found to depend strongly on relative quantities of reactants, nature of solvents used, temperature, and the presence of acid acceptors.

#### PUBLICATIONS/PATENTS

- 1) K. J. L. Paciorek, R. H. Kratzer, D. H. Harris, and M. E. Smythe, American Chemical Society meeting, April 8-13, 1984 (Polymer Preprints, 25 (1), 15-16 (1984)).
- 2) K. J. L. Paciorek, D. H. Harris, and R. H. Kratzer, "Boron-Nitrogen Polymers. I. Mechanistic Studies of Borazine Pyrolyses", J. Polym. Sci., in press.
- 3) K. J. L. Paciorek, R. H. Kratzer, D. H. Harris, M. E. Smythe, and P. F. Kimble, "Boron Nitride Preceramic Polymers", patent application No. 733,457, filed May 13, 1985.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input checked="" type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A/1	<del>DTIC</del>



**END**

**FILMED**

**10-85**

**DTIC**